

CELOTEX CW4000

Description

CELOTEX CW4000 is a rigid thermal insulation board made of polyisocyanurate (PIR) foam. The boards are provided on both sides with a low emissivity aluminium composite foil facing. **CELOTEX CW4000** is mainly used as thermal insulation in parial fill cavity wall application.

Packing & Storage

Thickness (mm)	Boards/ pack	m ² /pack	Boards/ pallet	m ² /pallet	Thermal resistance (R ₀) (m ² .K/W)
40	14	7,6	224	121,0	1,80
50	11	5,9	176	95,0	2,25
60	10	5,4	160	86,4	2,70
75	8	4,3	128	69,1	3,40
85	7	3,8	112	60,5	3,85
100	6	3,2	96	51,8	4,50

Store the boards on a flat surface, keep dry and protected from sunlight.

Characteristics

Thermal conductivity - λ_D (W/(m.K)) (EN 12667)	$40 \leq d \leq 100$ mm	0,022
Length (mm) (EN 822)		1200 ± 7,5
Width (mm) (EN 822)		450 ± 5
Thickness tolerance - d_N (EN 823)		T2
Density (kg/m ³)		NPD
Edge profile		straight
Compressive strength at 10 % deformation (kPa) (EN 826)		CS(10\Y)120
Dimensional stability (%) (EN 1604)		DS(70,90)3 DS(-20,-)1
Long term water absorption by total immersion (%) (EN 12087)		NPD
Reaction to fire (EN 13501-1)		F
Water vapour diffusion resistance - μ (EN 12086)		NPD
Tensile strength perpendicular to faces (kPa) (EN 1607)		NPD
Durability of compressive creep against ageing/degradation (kPa) (EN 1606)		NPD

NPD = no performance determined

Installation

Always consult the local regulations and contact the manufacturer for technical questions. Immediately after installation the insulation boards must be protected against weather conditions and sunlight.

Certifications

- **BBA 16/5343 (UK)**

Special indications

Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

Contact: www.soprema.com